



Accura[®] Xtreme[™] White 200

Xtreme Class

Ultra tough white plastic to replace CNC machined polypropylene and ABS articles

Post-Cured Material

MEASUREMENT	CONDITION	METRIC	U.S.
Tensile Strength (MPa/PSI)	ASTM D 638	45-50	6530-7250
Tensile Modulus (MPa/KSI)	ASTM D 638	2300-2630	334-381
Elongation at Break (%)	ASTM D 638	7-20	7-20
Flexural Strength (MPa/PSI)	ASTM D 790	75-79	10880-11460
Flexural Modulus (MPa/KSI)	ASTM D 790	2350-2550	341-370
Impact Strength (J/m /Ft-lbs/in)	ASTM D 256	55-66	1.03-1.24
Heat Deflection Temperature	ASTM D 648 @ 66 PSI @ 264 PSI	47 42	117 108
Coefficient of Thermal Expansion (CTE)	ASTM E 831-93 30-50 °C 70-140 °C	95 180	53 100
Water Absorption (%)	ASTM D 570-98	0.38	0.38
Glass Transition (Tg)	DMA, E"	52	126
Hardness, Shore D		78-80	78-80

Liquid Material

MEASUREMENT	CONDITION	VALUE
Viscosity	@ 30 °C (86 °F)	650-750 cps
Penetration Depth (Dp)		4.6 mils
Critical Exposure (Ec)		8.3 mJ/cm ²
Color		White
Solid Density	@ 25 °C (77 °F)	1.18 g/cm ³
Liquid Density	@ 25 °C (77 °F)	1.12 g/cm ³

Features

- Exceptionally tough and durable
- Resists breakage and handles challenging functional assemblies
- Great for snap fits, assemblies and demanding applications
- Ideal for master patterns for vacuum casting



www.3dsystems.com

UK
Tel: +44 1442 282 600
info@3dsystems-europe.com

**Germany, Scandinavia,
Eastern Europe, Middle East**
Tel: +49 6151 357 0
info@3dsystems-europe.com

USA
Tel: +1 803.326.3900
moreinfo@3dsystems.com

Asia-Pacific
Melbourne Tel: +61 3 9819 4422
Sydney Tel: +61 2 9516 5571
3dprinters.asiapac@3dsystems.com

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2017 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. Xtreme is a trademark and the 3D logo and Accura are registered trademarks of 3D Systems, Inc.