



Accura[®] ABS Black (SL 7820)

Simulate and replace CNC-machined black ABS articles

Post-Cured Material Details

MEASUREMENT	CONDITION	METRIC	U.S.
Tensile Strength (MPa/PSI)	ASTM D 638	45-47	6525-6815
Tensile Modulus (MPa/KSI)	ASTM D 638	1890-2440	274-354
Elongation at Break (%)	ASTM D 638	6-13	6-13
Flexural Strength (MPa/PSI)	ASTM D 790	75-78	10875-11310
Flexural Modulus (MPa/KSI)	ASTM D 790	2260-2370	328-344
Impact Strength (J/m /Ft-lbs/in)	ASTM D 256	39-56	0.73-1.05
Heat Deflection Temperature	ASTM D 648 @ 66 PSI	51 °C	124 °F
Coefficient of Thermal Expansion (CTE) (µm/m-°C / µm/in-°F)	ASTM E 831-93 25-50 °C	93	52
Glass Transition (Tg)	DMA, E''	62 °C	144 °F
Hardness, Shore D		86	86

Features

- Rigid and tough
- Functional assemblies
- Short-run production parts

Liquid Material Details

MEASUREMENT	CONDITION	Value
Viscosity	@ 30 °C (86 °F)	210 cps
Penetration Depth (Dp)		4.5 mils
Critical Exposure (Ec)		10 mJ/cm ²
Color		Black
Solid Density	@ 25 °C (77 °F)	1.16 g/cm ³
Liquid Density	@ 25 °C (82 °F)	1.13 g/cm ³

contact@quickparts.com | www.quickparts.com

©2023. All rights reserved. Specifications subject to change without notice.



North America
+1 931 766 7290

United Kingdom
+44 (0) 1494 479 690

Germany
+49 (0) 6073 689 6000

France
+33 (0) 2 43 51 20 30

Italy
+39 0121 390310

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. Quickparts makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use