



Makrolon[®] 2407

MVR (300°C/1.2 kg) 19 cm³/10 min; general purpose; low viscosity; UV stabilized; easy release; injection molding - melt temperature 280 - 320°C; available in transparent, translucent and opaque colors

Physical Properties

MEASUREMENT	CONDITION	Value
Density (73°F)	ISO 1183	1.20g/cm ³
Apparent (Bulk) Density ³	ISO 60	0.66g/cm ³
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	ISO 1133	20g/10 min
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	ISO 1133	19cm ³ /10min
Molding Shrinkage		
Across Flow	ISO 2577	0.50 to 0.70%
Flow	ISO 2577	0.50 to 0.70%
Across Flow : 536°F, 0.0787 in ⁴	ISO 294-4	0.70%
Flow : 0.0787 in ⁴	ISO 294-4	0.65%
Water Absorption		
Saturation, 73°F	ISO 62	0.30%
Equilibrium, 73°F, 50% RH		0.12%

Hardness Properties

MEASUREMENT	CONDITION	Value
Ball Indentation Hardness	ISO 2039-1	16800 psi

Mechanical Properties

MEASUREMENT	CONDITION	Value
Tensile Modulus (73°F)	ISO 527-1/1	348000 psi
Tensile Stress		
Yield, 73°F	ISO 527-2/50	9570 psi
Break, 73°F		9430 psi

Features

- General Purpose
- Good Mold Release
- Low Viscosity
- UV Stabilized

Processing Method

- Injection Molding

Applications

- General Purpose

Colors

- Clear/Transparent
- Colors Available
- Opaque
- Translucent

contact@quickparts.com | www.quickparts.com

©2023. All rights reserved. Specifications subject to change without notice.

Makrolon® 2407

Mechanical Properties (continued)

MEASUREMENT	CONDITION	Value
Tensile Strain Yield, 73°F Break, 73°F	ISO 527-2/50	6.0% 120%
Nominal Tensile Strain at Break (73°F)	ISO 527-2/50	> 50%
Tensile Creep Modulus 1 hr 1000 hr	ISO 899-1	319000 psi 276000 psi
Flexural Modulus ⁵ (73°F)	ISO 178	341000 psi
Flexural Stress ⁵ 73°F 3.5% Strain, 73°F	ISO 178	14200 psi 10700 psi
Flexural Strain at Flexural Strength ⁶ (73°F)	ISO 178	7.0%

Films

MEASUREMENT	CONDITION	Value
Water Vapor Transmission Rate (73°F, 85% RH, 3.9 mil)	ISO 15106-1	0.97g/100 in ² /24 hr
Carbon Dioxide Permeability (73°F, 1.0 mil)	ISO 2556	18900cm ³ /m ² /bar/24 hr
Gas Permeation Carbon Dioxide : 3.9 mil Nitrogen : 1.0 mil Nitrogen : 3.9 mil Oxygen : 1.0 mil Oxygen : 3.9 mil	ISO 2556	4800cm ³ /m ² /bar/24 hr 630cm ³ /m ² /bar/24 hr 160cm ³ /m ² /bar/24 hr 3150cm ³ /m ² /bar/24 hr 800 cm ³ /m ² /bar/24 hr

Impact Properties

MEASUREMENT	CONDITION	Value
Charpy Notched Impact Strength ⁷ -22°F, Complete Break 73°F, Partial Break	ISO 179/1eA	6.7ft-lb/in ² 31ft-lb/in ²
Charpy Unnotched Impact Strength -76°F -22°F 73°F	ISO 179/1eU	No Break No Break No Break

contact@quickparts.com | www.quickparts.com

©2023. All rights reserved. Specifications subject to change without notice.

North America
+1 931 766 7290

United Kingdom
+44 (0) 1494 479 690

Germany
+49 (0) 6073 689 6000

France
+33 (0) 2 43 51 20 30

Italy
+39 0121 390310

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. Quickparts makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

Makrolon® 2407

Impact Properties (continued)

MEASUREMENT	CONDITION	Value
Notched Izod Impact Strength ⁷ -22°F, Complete Break 73°F, Partial Break	ISO 180/A	5.7ft·lb/in ² 31ft·lb/in ²
Multi-Axial Instrumented Impact Energy -22°F 73°F	ISO 6603-2	47.9ft·lb 40.6ft·lb
Multi-Axial Instrumented Impact Peak Force -22°F 73°F	ISO 6603-2	1350lbf 1150lbf

Thermal Properties

MEASUREMENT	CONDITION	Value
Deflection Temperature Under Load 66 psi, Unannealed 264 psi, Unannealed	ISO 75-2/B ISO 75-2/A	277°F 255°F
Glass Transition Temperature ⁸	ISO 11357-2	289°F
Vicat Softening Temperature -- --	ISO 306/B120 ISO 306/B50	293°F 289°F
Ball Pressure Test (277°F)	IEC 60695-10-2	Pass
CLTE Flow : 73 to 131°F Transverse : 73 to 131°F	ISO 11359-2	3.6E-5in/in/°F 3.6E-5in/in/°F
Thermal Conductivity ⁹ (73°F)	ISO 8302	1.4 Btu·in/hr/ft ² /°F
RTI Elec (0.06 in)	UL 746B	257°F
RTI Imp (0.06 in)	UL 746B	259°F
RTI Str (0.06 in)	UL 746B	257°F

Electrical Properties

MEASUREMENT	CONDITION	Value
Surface Resistivity	IEC 60093	1.0E+16 ohms
Volume Resistivity (73°F)	IEC 60093	1.0E+16 ohms·cm

contact@quickparts.com | www.quickparts.com

©2023. All rights reserved. Specifications subject to change without notice.

North America
+1 931 766 7290

United Kingdom
+44 (0) 1494 479 690

Germany
+49 (0) 6073 689 6000

France
+33 (0) 2 43 51 20 30

Italy
+39 0121 390310

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. Quickparts makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

Makrolon® 2407

Electrical Properties (continued)

MEASUREMENT	CONDITION	Value
Electric Strength (73°F, 0.0394 in)	IEC 60243-1	860 V/mil
Relative Permittivity 73°F, 100 Hz 73°F, 1 MHz	IEC 60250	3.10 3.00
Dissipation Factor 73°F, 100 Hz 73°F, 1 MHz	IEC 60250	5.0E-4 9.0E-3
Comparative Tracking Index Solution A Solution B	IEC 60112	250 V 125 V

Flammability Properties

MEASUREMENT	CONDITION	Value
Flame Rating 0.11 in 0.030 in	UL 94	HB V-2
Glow Wire Flammability Index 0.030 in 0.060 in 0.12 in	IEC 60695-2-12	1560°F 1610°F 1710°F
Glow Wire Ignition Temperature 0.030 in 0.04 in 0.06 in 0.12 in	IEC 60695-2-13	1610°F 1610°F 1610°F 1610°F
Oxygen Index ¹⁰	ISO 4589-2	27%
Application of Flame from Small Burner ¹¹ (78.7 mil)	DIN 53438-1, -3	K1, F1
Burning Rate ¹² (> 39.4 mil)	ISO 3795	passed
Flash Ignition Temperature	ASTM D1929	896°F
Needle Flame Test 59.1 mil ¹³ 59.1 mil ¹⁴ 78.7 mil ¹³ 78.7 mil ¹⁴ 0.12 in ¹³ 0.12 in ¹⁴	IEC 60695-11-5	5.0 sec 60.0 sec 5.0 sec 120.0 sec 10.0 sec 120.0 sec

contact@quickparts.com | www.quickparts.com

©2023. All rights reserved. Specifications subject to change without notice.

North America
+1 931 766 7290

United Kingdom
+44 (0) 1494 479 690

Germany
+49 (0) 6073 689 6000

France
+33 (0) 2 43 51 20 30

Italy
+39 0121 390310

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. Quickparts makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

Makrolon® 2407

Flammability Properties (continued)

MEASUREMENT	CONDITION	Value
Self Ignition Temperature	ASTM D1929	1022°F

Optical Properties

MEASUREMENT	CONDITION	Value
Refractive Index ¹⁵	ISO 489	1.584
Light Transmittance		
39.37 mil		89.0%
78.74 mil	ISO 13468-2	89.0%
118.1 mil		88.0%
157.5 mil		87.0%
Haze (118.1 mil)	ISO 14782	< 0.800%

Additional Information

MEASUREMENT	CONDITION	Value
Electrolytical Corrosion (73°F)	IEC 60426	A1

Injection Properties

MEASUREMENT	Value
Drying Temperature - Dry Air Dryer	248°F
Drying Time - Dry Air Dryer	2.0 to 3.0hr
Suggested Max Moisture	< 0.020%
Suggested Shot Size	30 to 70%
Rear Temperature	482 to 500°F
Middle Temperature	518 to 536°F
Front Temperature	536 to 554°F
Nozzle Temperature	554 to 572°F
Processing (Melt) Temp	536 to 608°F

contact@quickparts.com | www.quickparts.com

©2023. All rights reserved. Specifications subject to change without notice.



North America
+1 931 766 7290

United Kingdom
+44 (0) 1494 479 690

Germany
+49 (0) 6073 689 6000

France
+33 (0) 2 43 51 20 30

Italy
+39 0121 390310

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. Quickparts makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

Makrolon® 2407

Injection Properties (continued)

MEASUREMENT	Value
Mold Temperature	176 to 248°F
Back Pressure	725 to 2180 psi
Vent Depth	9.8E-4 to 3.0E-3 in
Hold Pressure (% of Injection Pressure)	300°C
Peripheral Screw Speed	50 - 75%
Standard Melt Temperature	0.05 - 0.2 m/s

Notes

³Pellets

⁴60x60x2mm, 500 bar

⁵0.079 in/min

⁶2.0 mm/min

⁷3 mm

⁸10°C/min

⁹Across Flow

¹⁰Procedure A

¹¹Method K and F

¹²US-FMVSS

¹³Method K

¹⁴Method F

¹⁵Method A

contact@quickparts.com | www.quickparts.com

©2023. All rights reserved. Specifications subject to change without notice.



North America
+1 931 766 7290

United Kingdom
+44 (0) 1494 479 690

Germany
+49 (0) 6073 689 6000

France
+33 (0) 2 43 51 20 30

Italy
+39 0121 390310

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. Quickparts makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.