



Contact Us  
Aluminum 6063-T5

**Subcategory:** 6000 Series Aluminum Alloy; Aluminum Alloy; Metal; Nonferrous Metal

**Close Analogs:**

**Composition Notes:**

Aluminum content reported is calculated as remainder.

Composition information provided by the Aluminum Association and is not for design.

**Key Words:** UNS A96063; ISO AIMg0.5Si; Aluminium 6063-T5; AA6063-T5

Component	Wt. %	Component	Wt. %	Component	Wt. %
Al	Max 97.5	Mg	0.45 - 0.9	Si	0.2 - 0.6
Cr	Max 0.1	Mn	Max 0.1	Ti	Max 0.1
Cu	Max 0.1	Other, each	Max 0.05	Zn	Max 0.1
Fe	Max 0.35	Other, total	Max 0.15		



**Material Notes:**

Data points with the AA note have been provided by the Aluminum Association, Inc. and are NOT FOR DESIGN.

Physical Properties	Metric	English	Comments
Density	2.7 g/cc	0.0975 lb/in <sup>3</sup>	AA; Typical
<b>Mechanical Properties</b>			
Hardness, Brinell	60	60	AA; Typical; 500 g load; 10 mm ball
Hardness, Knoop	83	83	Converted from Brinell Hardness Value
Hardness, Vickers	70	70	Converted from Brinell Hardness Value
Ultimate Tensile Strength	186 MPa	27000 psi	AA; Typical
Tensile Yield Strength	145 MPa	21000 psi	AA; Typical
Elongation at Break	12 %	12 %	AA; Typical; 1/16 in. (1.6 mm) Thickness
Modulus of Elasticity	68.9 GPa	10000 ksi	AA; Typical; Average of tension and compression. Compression modulus is about 2% greater than tensile modulus.
Poisson's Ratio	0.33	0.33	
Fatigue Strength	68.9 MPa	10000 psi	AA; 500,000,000 cycles completely reversed stress; RR Moore machine/specimen
Shear Modulus	25.8 GPa	3740 ksi	

Shear Strength	117 MPa	17000 psi	AA; Typical
----------------	---------	-----------	-------------

**Electrical Properties**

Electrical Resistivity	3.16e-006 ohm-cm	3.16e-006 ohm-cm	AA; Typical at 68°F
------------------------	------------------	------------------	---------------------

**Thermal Properties**

CTE, linear 68°F	23.4 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	13 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	AA; Typical; Average over 68-212°F range.
------------------	--	--	---

CTE, linear 250°C	25.6 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	14.2 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	Average over the range 20-300°C
-------------------	--	--	---------------------------------

Specific Heat Capacity	0.9 J/g·°C	0.215 BTU/lb·°F
------------------------	------------	-----------------

Thermal Conductivity	209 W/m·K	1450 BTU-in/hr-ft <sup>2</sup> ·°F	AA; Typical at 77°F
----------------------	-----------	------------------------------------	---------------------

Melting Point	616 - 654 °C	1140 - 1210 °F	AA; Typical range based on typical composition for wrought products 1/4 inch thickness or greater
---------------	--------------	----------------	---

Solidus	616 °C	1140 °F	AA; Typical
---------	--------	---------	-------------

Liquidus	654 °C	1210 °F	AA; Typical
----------	--------	---------	-------------

**Processing Properties**

Annealing Temperature	413 °C	775 °F	hold at temperature for 2 to 3 hr; cool at 50°F per hour from 775 to 500°F
-----------------------	--------	--------	--

Solution Temperature	521 °C	970 °F
----------------------	--------	--------

Aging Temperature	182 °C	360 °F	hold at temperature fo
-------------------	--------	--------	------------------------

Aging Temperature	204 °C	400 °F	hold at temperature fo
-------------------	--------	--------	------------------------

**References for this datasheet.**

Some of the values displayed above may have been converted from their original units and/or rounded in order to display the information in a consistent format. Users requiring more precise data for scientific or engineering calculations can click on the property value to see the original value as well as raw conversions to equivalent units. We advise that you only use the original value or one of its raw conversions in your calculations to minimize rounding error. We also ask that you refer to MatWeb's disclaimer and terms of use regarding this information. MatWeb data and tools provided by MatWeb, LLC.